


## **RDZ TECHNICAL SHEET**



## **ZERO AD - LEVEL PANEL**

Thermoformed panel with regenerated plastic film, thickness 1 mm, to improve its resistance to the deformation of the walking surface. These panels have a tongue along the perimeter to connect them for proper combination. They have a moulded surface with reliefs of 16 mm so that the crosslinked polyethylene pipes Ø 14 mm can be fitted into the tabs of the panel at spacing of 40.5 mm or multiples.



Panel Features			
Features	Value	Unit	Standard
Dimensions	1215x810x18	mm	
Thickness	1	mm	
Fluidity Index	4 ÷ 6	g/10min	ISO 1133
Vicat softening temperature	99	°C	ISO 306
Density at 23°C	1.02 ÷ 1.05	g/cm³	ASTM D792
Izod Impact Resistance at 23 °C	6 ÷ 8	KJ/m²	ISO 180
Glue Specifications			
Features	Value	Unit	Method
Viscosity according to Brookfield parameters at 160 °C	5.500	mPa/s	ICAT MI 13
Softening temperature	80	°C	ICAT MI 12
Open time at 160 °C	Limitless	S	ICAT MI 10

